

Data Sheet - CHROMOMAT 15% RECYCLED

Description	Specification	Unit	Technical detail												
			90	100	115	130	150	170	200	230	250	280	300	350	400
Substance	ISO 536	g/m ²	90	100	115	130	150	170	200	230	250	280	300	350	400
Bulk	ISO 534	cm ³ /g	0.86	0.86	0.85	0.87	0.88	0.91	0.91	0.97	0.94	1.00	0.99	1.01	1.04
Gloss 75°	TAPPI T480	%	19	19	19	19	19	19	19	19	19	19	19	19	19
CIE whiteness	ISO 11475	%	124	124	124	124	124	124	124	124	124	124	124	124	124
Opacity	ISO 2471	%	89.8	93.5	94.0	95.4	96.9	98.0	99.2	99.2	99.9	100.2	100.2	100.3	100.3
Dynamic stiffness MD	ISO 5629	mN.m	0.30	0.40	0.60	0.80	1.30	2.10	3.20	5.4	6.60	12.80	12.80	20.70	34.30
Dynamic stiffness CD	ISO 5629	mN.m	0.16	0.22	0.36	0.60	0.80	1.30	2.10	3.70	4.40	8.80	8.80	14.40	22.70

dated : 12/02/2009