

# Horizon

## Pulpboard

### data sheet

Description	Standard	Unit	Target Values					
			200	230	230 <sub>matt</sub>	250	280	380
Thickness	-	Microns	200	230	230 <sub>matt</sub>	250	280	380
Grammage	-	GSM	150	170	150	188	210	285
Stiffness taber 15°	ISO 2493	MD mNm	1.5	2.4	2.2	3.3	4.5	10.3
Stiffness taber 15°	ISO 2493	CD mNm	1.0	1.7	1.5	2.2	2.9	6.0
CIE Whiteness	ISO 11475	D65 (UV inc)	152	152	152	152	152	152
Smoothness - Bendtsen	ISO 8791-2	ml/min	450	450	850	450	450	450



The mark of responsible forestry

April 2011

