

Data Sheet - Paperperfect Offset

Description	Specification	Unit	Technical detail (target specification)				
			60	70	75	90	104
Substance	ISO 536	g/m ²	60	70	75	90	104
Thickness	ISO 534	micron	81	95	101	122	135
Bendtsen Smoothness	ISO 8791-2	mL/min	180	220	220	240	190
ISO Opacity	ISO 2471	%	86	90	92	95	96
ISO Brightness	ISO 2470	%	98	98	98	98	98
CIE whiteness	ISO 11475	n ^o	160	160	160	160	160

Alkaline wood free offset paper, made from 100% ECF bleached eucalyptus pulp.

dated : April 2009