

## Cyber Premium GC2

Description	Standard	Unit	Values													
			200	210	240	250	260	270	280	300	310	320	330	350	360	380
Weight	T-410	gsm (g/m <sup>2</sup> )	200	210	240	250	260	270	280	300	310	320	330	350	360	380
Thickness	T-411	microns (µm)	330	346	398	417	437	470	490	532	553	571	592	631	648	684
Stiffness Taber 15° MD	T-489	mNm	6.8	7.7	12.7	15.1	16.7	19.2	21.8	26.6	29.0	30.4	33.2	39.9	43.2	48.9
Stiffness Taber 15° CD	T-489	mNm	3.4	3.8	6.3	7.5	8.4	9.6	10.9	13.3	14.5	15.2	16.6	19.9	21.6	24.4
Ply Bond (avg.)	T-569	J/m <sup>2</sup>	150													
Roughness PPS (top)	T-555	µm	2.1					2.3					2.5			
Brightness ISO (top)	T-452	%	85 min													
Whiteness CIE (top)	T-560	%	85 min													
Surface Strength IGT Pick (top)	ISO 3782/3	m/sec	0.7 min													
Gloss 75° (top)	T-480	%	35													
Moisture	T-412	%	6.0-7.5							7.0-8.5						
Cobb (top)	T-441	g/m <sup>2</sup>	50													
Cobb (back)	T-441	g/m <sup>2</sup>	100													

### Product Certifications

FSC®

Food safe (Robinson compliant)

### Mill Certifications

SO 9001

ISO 14001

OHSAS 18001

BRC