

## DCP

| Data sheet      | Specification | Unit                    | Technical detail |      |      |      |      |      |      |      |      |
|-----------------|---------------|-------------------------|------------------|------|------|------|------|------|------|------|------|
| Grammage        | ISO 536       | gsm (g/m <sup>2</sup> ) | 90               | 100  | 120  | 160  | 200  | 250  | 300  | 350  | 400  |
| Thickness       | ISO 534       | microns (µm)            | 99               | 110  | 128  | 160  | 200  | 230  | 276  | 322  | 370  |
| Bulk            | ISO 534       | cm <sup>3</sup> /g      | 1.10             | 1.10 | 1.07 | 1.00 | 1.00 | 0.92 | 0.92 | 0.92 | 0.92 |
| Whiteness CIE   | ISO 11475     | %                       | 170              |      |      |      |      |      |      |      |      |
| Opacity         | ISO 2471      | %                       | 95               | 96   | 97   | 99   |      |      |      |      |      |
| Bekk Smoothness | ISO 5627      | s                       | 150              |      |      |      | 140  | 125  | 110  |      |      |

### Product Certifications

FSC®  
 Colorlok Technology  
 EU Ecolabel  
 ISO 9706  
 DIN/EN 12281

### Mill Certifications

ISO 9001  
 ISO 14001  
 ISO 50001