

Elephant Greyboard

Unlined & Laminated Greyboards

Description	Standard	Unit	Values											
Product			Elephant Greyboard				Elephant Greyboard Extra							
Thickness	ISO 534	microns (µm)	500	750	1000	1200	1500	1700	2000	2300	2500	3000	3500	4000
Weight	ISO 536	gsm (g/m ²)	315	472	630	756	945	1071	1260	1449	1575	1890	2205	2520
Moisture	ISO 287	%	8.25				7.5							
Bulk	ISO 534	cm ³ /g	1.59											

White Lined Greyboards

Description	Standard	Unit	Values			
Thickness	ISO 534	microns (µm)	1200	1500	1700	2000
Weight	ISO 536	gsm (g/m ²)	768	975	1088	1290
Moisture	ISO 287	%	8.25	7	8.25	7
Bulk	ISO 534	cm ³ /g	1.56	1.54	1.56	1.55

Black Lined Greyboards

Description	Standard	Unit	Values
Thickness	ISO 534	microns (µm)	1500
Weight	ISO 536	gsm (g/m ²)	960
Moisture	ISO 287	%	8.25
Bulk	ISO 534	cm ³ /g	1.56