

Magno Volume

	Specification	Unit	Target					
			90	100	115	130	150	170
Grammage	ISO 536	gsm	90	100	115	130	150	170
Thickness	ISO 534	µm	97	108	124	140	162	184
Brightness (illuminant D65/10°)	ISO 2470-2	%	100	100	100	100	100	100
CIE Whiteness (D65/10°)	ISO 11475	%	124	125	126	126	126	126
Opacity	ISO 2471	%	94	95	96	97	98	98
Gloss TAPPI 75°	ISO 8254-1	%	14	14	14	14	14	14
Roughness PPS	ISO 8791-4	µm	4.5	4.5	4.5	4.5	4.5	4.5
Bulk	ISO 534	cm ³ /g	1.08	1.08	1.08	1.08	1.08	1.08
Relative Humidity (23°C)	TAPPI 502	%	50	50	50	50	50	50

Product Certifications

FSC®

Mill Certifications

ISO 9001

ISO 14001

OHSAS 18001