

Multiboard® EcoKraft

Description	Standard	Unit	Values								
Thickness	ISO 534	microns (µm)	405	445	480	515	550	585	630	660	695
Weight	ISO 536	gsm (g/m ²)	300	325	350	375	400	425	450	475	500
Bending Moment Taber 15° MD	T-489	mNm	16.2	20.3	24.9	29.9	36.0	43.0	50.7	57.0	65.1
Bending Moment Taber 15° CD	T-489	mNm	5.8	7.2	8.9	10.9	13.0	15.0	17.9	19.8	22.7
Brightness R457	ISO 2470	%	79								
Whiteness D65/10	ISO 11475	%	84								
Cobb 180 (reverse side)		g/m ²	40								

ISO 9001
ISO 14001