

Multiprint HS

Description	Standard	Unit	Values												
Substance	ISO 536	gsm (g/m ²)	300	325	350	375	400	425	450	475	500	525	550	575	600
Thickness	ISO 534	microns (µm)	405	440	475	505	540	575	610	640	675	710	745	775	810
Taber Stiffness 15° - MD	ISO 2493	mNm	11	14	19	24	28	33	40	46	53	59	66	72	79
Taber Stiffness 15° - CD	ISO 2493	mNm	4	5	8	9	11	13	15	18	20	23	27	30	34
Brightness - top side	DIN 53145	%	82%												
Cobb 60 - top side	-	g/m ²	60g/m ²												
Cobb 180 Reverse Side	-	g/m ²	50g/m ²												

FSC® certified