

WestRock PrintKote®

Description	Method	Unit	Values					
Thickness	T-411	microns (µm)	356	406	457	508	610	711
Weight	T-410	gsm (g/m ²)	265	295	325	345	405	460
Stiffness Taber 15° MD	T-489	mNm	11.8	16.7	21.6	27.5	43.1	53.9
Stiffness Taber 15° CD	T-489	mNm	5.9	9.3	11.8	15.2	22.6	28.4
Moisture	T-412	%	5.3	5.6	5.6	5.6	5.6	5.6
Internal Bond	T-569	J/m ²	147	147	147	158	168	168
GE Brightness (coated side)	T-452	%	86					
Parker Print (coated side)	T-555	µm	1.0	1.1	1.1	1.2	1.2	1.2
ZDT	T-541	kPa	324	310	276	276	276	276

PEFC certified

ISO 9001