

Proxima Plus

Description	Specification	Unit	Technical detail						
			350	385	420	460	510	560	610
Thickness	ISO 534	microns (µm)	350	385	420	460	510	560	610
Weight	ISO 536	gsm (g/m ²)	215	235	250	270	295	325	350
Stiffness (15°) CD	ISO 2493	mNm	5.32	7.05	8.31	10.8	15.2	17.8	24.5
Stiffness (15°) MD	ISO 2493	mNm	9.48	12.6	15.8	20.9	29.3	32.2	40.0
Moisture	ISO 287	%	7.0						
Roughness - top	ISO 8791-4	µm	1.5						
Brightness D65/10 - top	ISO 2470-1	%	82.0						
Gloss - top	Tappi T480	%	40						
IGT - top	ISO 8254-1	m/s	1.20						
Cobb 180s - top/middle/back	ISO 535	g/m ²	60						
Scott Plybonding	Tappi T569	J/m ²	130						
Squareness	GB/T 451.1	mm	2.0						
Size Deviation	GB/T 451.1	mm	2.0						