

Soporset Offset

Description	Specification	Unit	Technical detail													
			70	75	80	90	100	110	120	135	150	170	190	250	300	350
Basis Weight	ISO 536	gsm (g/m ²)	70	75	80	90	100	110	120	135	150	170	190	250	300	350
Thickness	ISO 534	microns (µm)	92	95	106	116	128	141	150	159	175	196	222	295	350	400
Bulk		µm/ g/m ²	1.31	1.27	1.33	1.29	1.28	1.28	1.25	1.17	1.17	1.18	1.18	1.18	1.18	1.18
CIE Whiteness	ISO 11475	%	161	161	161	161	161	161	161	161	161	161	161	161	161	161
Opacity	ISO 2471	%	91	92	94	95	96	97	98	98	98	99	100	100	100	100
Bendtsen Roughness	ISO 8791/2	ml/min	150	180	150	150	150	150	150	150	150	180	180	180	200	200
Moisture	ISO 287	%	6.2	6.2	6.0	6.0	6.0	5.8	5.8	6.5	6.5	6.5	6.5	6.5	6.5	6.5

FSC® certified

ISO 9001
 ISO 14001
 OHSAS 18001
 Chlorine Free
 EU EcoLabel