

Tambrite™ HS

Description	Standard	Unit	Values										
Thickness	ISO 534	microns (µm)	350	375	400	420	440	460	480	500	540	600	650
Weight	ISO 536	gsm (g/m²)	200	210	220	230	240	250	260	270	285	310	335
Bending Moment Taber 15° MD	ISO 2493	mNm	9.0	10.7	12.4	14.3	16.2	18.1	20.5	23.0	27.6	35.5	43.7
Bending Moment Taber 15° CD		mNm	5.0	5.9	6.8	7.8	8.8	9.8	11.0	12.3	14.6	18.5	22.4
Moisture	ISO 287	%	8.0								8.5		9.0
ISO Brightness C/2° (top side)	ISO 2470-1	%	86										
Surface Smoothness PPS 10 (top side)	ISO 8791-4	µm	1.2										
Scott Bond	T-569	J/m²	130										
Robinson Chocolate Test	EN 1230-2		max. 0.5 for one year storage in reels/pallets										

FSC® certified

ISO 9001
ISO 14001
FSC 22000
OHSAS 18001
ISO 50001