

Triplex Gris

Description	Standard	Unit	Values						
Thickness	ISO 534	microns (µm)	407	445	485	530	585	620	670
Weight	ISO 536	gsm (g/m ²)	300	325	350	375	425	450	475
Stiffness Taber 15° MD	ISO 2493	mNm	13.5	17.0	20.0	24.6	35.1	41.6	47.0
Stiffness Taber 15° CD	ISO 2493	mNm	6.0	7.5	8.8	10.8	15.4	18.2	20.5
Brightness (top side)	ISO 2470-2	%	79.5						
Bulk	ISO 534	cm ³ g	1.36	1.37	1.38	1.41	1.38	1.37	1.41

ISO 9001
 ISO 50001
 OHSAS 18001