

Uniboard-S

Description	Standard	Unit	Values								
			380	410	450	490	510	545	580	640	710
Thickness	ISO 534	microns (µm)	380	410	450	490	510	545	580	640	710
Weight	ISO 536	gsm (g/m ²)	300	320	350	380	400	425	450	500	550
Stiffness L&W 5° MD	DIN 53121	mNm	24.5	30.1	37.6	47.2	53.6	63.1	72.5	94.8	119.7
Stiffness L&W 5° CD	DIN 53121	mNm	9.1	11.3	14.6	18.7	21.5	26.1	30.6	41.1	50.7
Stiffness Taber 15° MD	T-489	mNm	12.9	15.3	18.8	23.3	26.5	30.9	35.3	45.3	56.1
Stiffness Taber 15° CD	T-489	mNm	4.3	5.4	7.1	8.7	10.2	12.5	14.9	20.0	24.5
Brightness	ISO 2470-02	%	81								
Cobb 60"		g/m ²	50								

ISO 9001
ISO 50001