

PRODUCT DATA

FASSON®

FASSON® High Gloss White FSC® Certified

Issued December 2023

Introduction

A self-adhesive paper sheet product for offset printing.

Description

Face: A premium-quality cast-coated woodfree offset paper, mirror finished glossy surface, white only. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

Availability

| | Adhesive ➡ | Permanent | Removable | Supertack | Deep Freeze |
|--|------------|-----------|-----------|-----------|-------------|
| Backing ⤴ | | | | | |
| Crack-Back® Plus (diagonal cracklines) | | X | X | X | |
| No cracklines | | X | | X | X |
| Scored backing* (parallel cracklines) | | X | | | |

* Parallel scored products have limitations compared to Crack-Back Plus, see reverse side.

Printing & Conversion

Offset printing

Before applying the label, the surface must be clean, dry, and grease-free.

Features:

Excellent lay flatness, enabling high-speed printing

The unique Crack-Back® Plus backing removal system with diagonal scored lines facilitates creating layouts, conversion, and application of the label.

Supertack adhesive is specifically developed for applications on rough and apolar surfaces.

Deep Freeze adhesive is specifically developed for labels to be applied at temperatures minus zero.

Uses:

Multi-colour-, identification-, mailing (addressing/shipping)-, carton-, packaging-, inventory-, pricing-, barcode labels. Promotional-, seasonal-, theme-, children's-, toy- and collectable stickers. Magazine supplements; on flat or curved surfaces.

For indoor use only.

General

Shelf life: 2 years stored at 20°C / 55% R.H.

For information regarding EHS regulation, please visit our website under downloads "Technical bulletins" TB 7.8 Product Compliance Fasson Offset" and for technical guidance "Technical bulletins" – Offset printing.

PRODUCT CHARACTERISTICS

Physical properties

Face

| | | |
|-----------------|---------------------------|------------|
| Basis weight: | 80 g/m ² | ISO 536 |
| Caliper: | 78 micron | ISO 534 |
| Tensile: | 4.3 kN/m MD / 2.7 kN/m CD | ISO 1924/2 |
| Brightness ISO: | 89 % | ISO 2470/2 |
| Gloss 20°: | 41 % | ISO 8254/3 |
| Opacity: | 92 % | ISO 2471 |

Adhesive

| | |
|--------------|--|
| Permanent: | General-purpose water-based permanent adhesive with a high initial tack and high adhesion on most common substrates. |
| Removable: | General-purpose emulsion-based removable adhesive. A well-balanced combination of tack and adhesion permits easy removability from most non-porous surfaces. Good UV-resistance and cold temperature performance. <u>Caution:</u> Removability can be inhibited if the label is applied to surfaces with which it could react, such as surfaces printed with nitrocellulose-based inks, varnishes, polystyrene, and certain coated papers and board (SBR based coatings). |
| Supertack: | A water-based permanent adhesive specially developed for apolar and rough surfaces. High initial tack combined with strong permanent bond. |
| Deep Freeze: | A water-based adhesive with very good low temperature performance which, in combination with an excellent initial tack and holding power, makes it highly suitable for deep freeze applications. At room temperature, labels are easily removable. |

| | Permanent | Removable | Supertack | Deep Freeze |
|--|-----------|-----------|-----------|-------------|
| Adhesion (N/m) (FTM 2 on steel/20 min. bond time) | 380 | 100 | 460 | 50 |
| Tack (N) (FTM 9 on glass) | 10.5 | 3.5 | 12.6 | 2.5 |
| Minimum application temperature | > +5 | > +5 | > +5 | > -20 |
| Service temperature range up to 24 hrs (°C) | +80 | +80 | +80 | +70 |
| up to 1 hr (°C) | +110 | +110 | +110 | |
| Resistance to cold (°C) ¹⁾ down to | -40 | -40 | -40 | -40 |

¹⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

Backing

| | |
|-------------------|---|
| Crack-Back® Plus: | One-side-coated bleached kraft paper, with diagonally crush-scored lines, along which the backing will crack cleanly when bent back, allowing easy removal in just two pieces. Lines are spaced just 32 mm apart. Good lay flatness ensures first-class printing and finishing. (For optimal functionality, take care of the following: minimum label size must be 20 cm ² . The shortest side of a rectangle or the smallest diameter of an ellipse must be at least 25 mm.) |
| No cracklines: | A bleached one-side-coated white kraft, especially designed for sheet products, featuring minimal moisture sensitivity. |
| Scored backing | One-side-coated bleached kraft paper, with crush-scored lines, running in the machine direction, 35 mm apart. Bending along one of the lines will crack the backing open for easy removal. The functionality of scored backing products is strongly related to label size. We advise not to use scored backing for labels larger than A4 (210 x 297 mm) or smaller than A8 (52 x 74 mm). Also, the direction of the score lines is of importance; for labels from A8 to A6 (105x 148 mm) it is commendatory to have the score lines parallel to the short side of the label. For products not complying to these recommendations Torraspapel - Lecta does not take responsibility for the functionality of the score lines. Use Crack-Back® Plus instead! |
| Basis weight: | 86 g/m ² (Crack-Back® Plus and Scored backing) / 80 g/m ² (No cracklines) |
| Caliper: | 87 micron (Crack-Back® Plus and Scored backing) / 81 micron (No cracklines) |

This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel - Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

Fasson® and Crack-Back® are registered trademarks of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.