



VISION

Colour Digital

data sheet

Description	Standard Used	Unit								
Grammage	ISO 536	GSM	90	100	120	160	200	250	300	350
Thickness	ISO 534	micron	98	109	125	158	196	250	300	350
Bulk	ISO 534		1.38	1.09	1.04	0.99	0.98	1.0	1.0	1.0
Moisture	ISO 287	%	4.5	4.5	4.7	4.7	4.6	4.5	-	-
Smoothness	ISO 5627	Bekk sec	130	140	140	140	135	100	75	75
Formation	Kajaani	Kajaani Index	110	110	110	110	110	110	110	110
Whiteness	ISO 11475	CIE	168	168	168	168	168	168	168	168
Opacity	ISO 2471	%	92	95	95	96	98	98	99	-
Stiffness-MD	ISO 2493	m/Π	125	165	255	455	700	1060	1500	2900
Stiffness - CD	ISO 2493	m/Π	65	85	145	260	400	640	940	1800



The mark of responsible forestry

March 2015

