

# AEGLE™ Pro

FULL MILL RANGE - bold lines indicate EBB stock range

Datasheet			Target Values															
Description	Standard	Unit																
Thickness	ISO 534	mic	300	320	340	<b>360</b>	<b>390</b>	<b>410</b>	<b>430</b>	<b>460</b>	<b>480</b>	<b>520</b>	<b>560</b>	<b>620</b>	670	<b>720</b>	760	
Grammage	ISO 536	g/m <sup>2</sup>	180	190	200	<b>210</b>	<b>225</b>	<b>235</b>	<b>245</b>	<b>260</b>	<b>270</b>	<b>290</b>	<b>310</b>	<b>340</b>	360	<b>380</b>	400	
Bending moment Taber 15° MD	ISO 2493	mNm	6.5	8.3	10.3	<b>12.4</b>	<b>14.4</b>	<b>16.4</b>	<b>18.6</b>	<b>22.0</b>	<b>24.6</b>	<b>30.5</b>	<b>36.4</b>	<b>45.0</b>	51	<b>61</b>	70	
Bending moment Taber 15° CD	ISO 2493	mNm	3.0	3.9	5.0	<b>5.9</b>	<b>7.2</b>	<b>8.2</b>	<b>9.3</b>	<b>11.0</b>	<b>12.3</b>	<b>15.5</b>	<b>18.5</b>	<b>22.0</b>	27	<b>31</b>	34	
Moisture	ISO 287	%	7.8	7.8	8.0	<b>8.0</b>	<b>8.0</b>	<b>8.0</b>	<b>8.0</b>	<b>8.5</b>	<b>8.5</b>	<b>8.7</b>	<b>9.0</b>	<b>9.0</b>	9.0	<b>9.0</b>	9.0	
ISO Brightness D65 top	ISO 2470	%	87	87	87	<b>87</b>	<b>87</b>	<b>87</b>	<b>87</b>	<b>87</b>	<b>87</b>	<b>87</b>	<b>87</b>	<b>87</b>	87	<b>87</b>	87	
Surface Smoothness PPS10	ISO 8791-4	µm	1.3	1.3	1.3	<b>1.3</b>	<b>1.3</b>	<b>1.3</b>	<b>1.3</b>	<b>1.3</b>	<b>1.3</b>	<b>1.3</b>	<b>1.3</b>	<b>1.3</b>	1.3	<b>1.3</b>	1.3	
Gloss 75°	ISO 8254-1	%	45	45	45	<b>45</b>	<b>45</b>	<b>45</b>	<b>45</b>	<b>45</b>	<b>45</b>	<b>45</b>	<b>45</b>	<b>45</b>	45	<b>45</b>	45	
Cobb 3 min top/back	ISO 535	g/m <sup>2</sup>	50	50	50	<b>50</b>	<b>50</b>	<b>50</b>	<b>50</b>	<b>50</b>	<b>50</b>	<b>50</b>	<b>50</b>	<b>50</b>	50	<b>50</b>	50	
Scott Bond	Tappi T569	J/m <sup>2</sup>	130	130	130	<b>130</b>	<b>130</b>	<b>130</b>	<b>130</b>	<b>130</b>	<b>130</b>	<b>130</b>	<b>130</b>	<b>130</b>	130	<b>130</b>	130	



Nov 2018

