

AEGLE™ White

This range is mill makings only, minimum 3 tonnes per item, 30-45 days.

Datasheet

Description	Standard	Unit	Target Values											
			285	305	325	355	375	395	425	445	470	500	550	600
Thickness	ISO 534	µm	285	305	325	355	375	395	425	445	470	500	550	600
Grammage	ISO 536	g/m ²	200	210	220	235	245	255	270	280	290	305	330	355
Bending moment Taber 15° MD	ISO 2493	mNm	6.0	7.7	9.7	12.0	14.0	16.0	19.0	20.8	23.3	27.0	34.0	41.0
Bending moment Taber 15° CD	ISO 2493	mNm	3.4	4.0	4.8	6.0	6.8	7.8	9.1	10.0	11.2	13.0	16.0	20.0
Moisture	ISO 287	%	8.0	8.0	8.0	8.0	8.0	8.5	8.5	8.7	8.7	9.0	9.0	9.0
ISO Brightness D65 top	ISO 2470	%	91	91	91	91	91	91	91	91	91	91	91	91
ISO Brightness D65 back	ISO 2470	%	86	86	86	86	86	86	86	86	86	86	86	86
Surface Smoothness PPS10	ISO 8791-4	µm	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
Gloss 75°	ISO 8254-1	%	45	45	45	45	45	45	45	45	45	45	45	45
Cobb 3 min top/back	ISO 535	g/m ²	50	50	50	50	50	50	50	50	50	50	50	50
Scott Bond	Tappi T569	J/m ²	130	130	130	130	130	130	130	130	130	130	130	130



The mark of responsible forestry

Dec 2020

EBB
PAPER
BOARD DIVISION