

Crescendo® C1S

data sheet										
Description	Standard Used	Unit	Technical Specification							
Grammage	T-410	GSM	200	230	260	280	300	325	350	410
Thickness	T-411	micron	254	305	345	376	406	452	493	597
Moisture	T-412	%	5.3	5.3	5.3	5.3	5.3	5.3	5.3	5.3
Internal Bond	Um-403	J/m2	160	150	150	150	150	150	150	150
Stiffness Taber 15° - MD	ISO 2493	mNm	5.4	8.3	11.0	13.9	17.1	21.6	26.4	42.2
Stiffness Taber 15° - CD	ISO 2493	mNm	2.5	4.4	5.5	6.9	8.4	11.0	13.3	22.6
ISO Brightness	ISO 2470	%	91	91	91	91	91	91	91	91
GE Brightness	T-452	%	92	92	92	92	92	92	92	92
CIE Whiteness	ISO 11475	%	122	122	122	122	122	122	122	122
Gloss	T-480	%	51	51	51	51	51	51	51	51
Parker Print	ISO 8791	µm	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
Robinson Test	EN 1230-2		Approved							



April 2015

