

CYBER PREMIUM

HARD SIZED

Data sheet

Description	Specification	Unit							
Thickness	Tappi T 411	µm	346	398	437	490	592	697	
Substance	Tappi T410	gsm	210	240	260	280	330	380	
Bending Resistance (Taber 15°) - MD	Tappi T 489	mNm	7.67	12.68	16.73	21.79	33.25	48.90	
Bending Resistance (Taber 15°) - CD	Tappi T 489	mNm	3.83	6.34	8.36	10.90	16.62	24.45	
Bending Resistance (Taber 15°) - GM	Tappi T 489	mNm	5.42	8.97	11.83	15.41	23.51	34.57	
Ply Bond (Avg.)	Tappi T 833	J/m ²	150 min						
Roughness PPS (Avg.) Top Side	Tappi T 555	µm	2.1		2.3		2.5		
Brightness ISO	Tappi T 452	%	85 min						
Whiteness CIE Top Side	Tappi T 560	%	85 min						
Surface Strength IGT Pick	ISO 3782 & 3783	m/sec	0.7 min						
Gloss at 75° (Avg.) Top Side	Tappi T 480	%	40 - 5 units						
Moisture Content	Tappi T 412	%	6.0 - 7.5				7.0 - 8.5		



The mark of responsible forestry

Dec 2018

