

FoldKraft™

Data sheet

Description	Standard Used	Unit						
Grammage	T-410	GSM	283	317	352	381	420	459
Thickness	T-411	micron	406	457	508	559	610	660
ZDT	T-541	psi	35	35	35	35	35	35
Stiffness Taber 15° - MD	T-489	mNm	20	27	34	43	53	64
Stiffness Taber 15° - CD	T-489	mNm	9	12	16	21	25	30
Elemendorf Tear: Dry - MD	T-414	gf	490	550	610	680	730	800
Elemendorf Tear: Dry - CD	T-414	gf	525	600	670	750	825	900
Smoothness	T-538	Sheffield	250	250	250	250	280	280



April 2017

