

sappi | GalerieArt Matt



Data Sheet	Specification	Unit	Target											
			80	90	100	115	130	150	170	200	250	300	350	400
Grammage	ISO 536	gsm	80	90	100	115	130	150	170	200	250	300	350	400
Thickness	ISO 534	µm	80	92	102	115	130	152	173	210	263	315	368	420
Brightness (illuminant D65/10°)	ISO 2470-2	%	99	99	99	99	99	99	99	99	99	99	100	100
CIE Whiteness (D65/10°)	ISO 11475	%	127	127	127	127	127	127	127	127	127	127	127	127
Opacity	ISO 2471	%	90.5	92	94	95.5	97	97.5	98	99	98	98	100	100
Gloss TAPPI 75°	ISO 8254-1	%	14	14	14	14	14	14	14	15	20	20	36	36
Roughness PPS	ISO 8791-4	µm	3.2	3.2	3.3	3.3	3.4	3.5	3.5	4.0	2.0	2.0	2.0	2.0
Bulk	ISO 534	cm³/g	1.00	1.00	1.00	1.00	1.00	1.01	1.02	1.05	1.05	1.05	1.05	1.05
Relative Humidity (23°C)	TAPPI 502	%	50	50	50	50	50	50	50	50	50	50	50	50



The mark of
responsible forestry
FSC® C008007

August 2020

