

Incada® Exel

data sheet

Description	Standard Used	Unit									
Grammage	ISO 536	GSM	200*	210*	225*	235	255	280	300	325	350*
Thickness	ISO 534	micron	310	340	375	400	450	490	540	590	640
Whiteness (printing side)	ISO 11475	%	120	120	120	120	120	120	120	120	120
Whiteness (reverse)	ISO 11475	%	97	97	97	97	97	97	97	97	97
Brightness (printing side)	ISO 2470	%	91.5	91.5	91.5	91.5	91.5	91.5	91.5	91.5	91.5
Brightness (reverse)	ISO 2470	%	86.0	86.0	86.0	86.0	86.0	86.0	86.0	86.0	86.0
Board Gloss 75°	ISO8254-1	%	50	50	50	50	50	50	50	50	50
Cobb	ISO 535	g/m ² 60 s	30	30	30	30	30	30	30	30	30
Bending Stiffness L&W 5° - MD	ISO 5628	mNm	15.8	20.1	26.3	29.4	38.4	49.2	60.4	77.4	91.4
Bending Stiffness L&W 5° - CD	ISO 5628	mNm	6.0	7.9	10.6	11.9	15.8	20.5	25.4	32.8	38.9
Bending Taber 15° - MD	ISO 2493	mNm	8.5	10.6	13.6	15.2	19.6	24.9	30.3	38.7	45.5
Bending Taber 15° - CD	ISO 2493	mNm	3.7	4.6	5.9	6.6	8.5	10.8	13.2	16.8	19.8

* makings only



The mark of
responsible forestry
FSC® C008007

January 2017

