

IndoKroma

Data sheet

Description	Specification	Unit							
Substance	Tappi T410	GSM	230	250	270	280	300	320	350
Caliper	Tappi T411	µm	354	384	421	440	510	552	612
Bending resistance (L&W) - MD	Tappi T556	mN	180	250	362	400	490	600	745
Bending resistance (L&W) - CD	Tappi T556	mN	88	125	180	200	245	302	375
Bending resistance (L&W) - GM	Tappi T556	mN	126	177	255	283	346	426	529
Poly substance	Mill method	GSM	20	20	20	20	20	20	20
Poly adhesion strength	Tappi T539	Points	3	3	3	3	3	3	3
Surface tension (back)	Tappi T698	Dynes/cm	38	38	38	38	38	38	38
Roughness - Bendsten (top)	ISO 8791-2	ml/min	50	50	50	50	50	50	50
Roughness - Bendsten (back)	ISO 8791-2	ml/min	300	300	300	300	300	300	300
Moisture content	Tappi T412	%	6	6	6	6	6	6	6
Surface strength IGT pick (top)	ISO 3782 & 3783	m/sec	0.7	0.7	0.7	0.7	0.7	0.7	0.7



The mark of responsible forestry

January 2017

