

Invercote® G

data sheet												
Description	Standard Used	Unit										
Grammage	ISO 536	GSM	180	200	220*	240	260	280	300	330	350	380
Thickness	ISO 534	micron	205	235	260	300	330	360	395	435	465	505
Opacity	ISO 2471	%	94.5	95.0	97.0	97.3	97.7	98.1	98.6	98.8	99.1	99.2
Whiteness (printing side)	ISO 11475	%	129	129	129	129	129	129	129	129	129	129
Whiteness (reverse)	ISO 11475	%	110	110	122	122	122	122	122	122	122	122
Brightness (printing side)	ISO 2470	%	94	94	94	94	94	94	94	94	94	94
Brightness (reverse)	ISO 2470	%	90	90	94	94	94	94	94	94	94	94
Board Gloss 75°	ISO8254-1	%	40	40	40	40	40	40	40	40	40	40
Cobb	ISO 535	g/m²60s	30	30	30	30	30	30	30	30	30	30
Bending Stiffness L&W 5° - MD	ISO 5628	mNm	5.5	8.2	11.9	16.2	20.8	29.9	38.5	50.8	61.8	77.9
Bending Stiffness L&W 5° - CD	ISO 5628	mNm	2.5	3.7	5.4	7.5	9.7	12.5	16.0	21.0	25.0	31.0
Bending Taber 15° - MD	ISO 2493	mNm	3.1	4.6	6.8	9.2	11.8	15.2	19.6	26.5	31.4	39.6
Bending Taber 15° - CD	ISO 2493	mNm	1.4	2.2	3.1	4.0	5.2	6.6	8.7	11.1	13.3	16.7

* making only



The mark of
responsible forestry
FSC® C008007

February 2015

