



INTERNATIONAL  PAPER

REY

The Conscious Choice

	Standard	Unit	Target				
Substance	ISO 536	gsm	80	90	100	120	160
Thickness	ISO 534	micron	100	109	114	133	176
Bulk	ISO 534		1.25	1.21	1.12	1.11	1.10
Roughness - Bendtsen	ISO 8791	ml/min	110	95	80	80	80
Smoothness - Bekk	ISO 5627	sec	55	60	65	65	65
Whiteness	ISO 11475	CIE	170	170	170	170	170
Brightness	ISO 2470-2	%	113	113	113	113	113
Opacity	ISO 2471	%	92	94	95	97	99
Stiffness - MD	ISO 2493	m/Newton	120	135	160	260	540
Stiffness - CD	ISO 2493	m/Newton	40	75	90	150	290



The mark of responsible forestry



EU Ecolabel
FR/011/002



ISO 9706
ARCHIVING



March 2020