

# Tango® Digital C1S

data sheet					
Description	Specification	Unit	Technical detail		
<b>Thickness</b>	<b>T 411</b>	<b>caliper</b>	<b>305</b>	<b>356</b>	<b>406</b>
Substance	T 410	gsm	235	265	295
Taber Stiffness - MD	T 489	gm/cm	85	115	170
Taber Stiffness - CD	T 489	gm/cm	45	55	90
Internal Bond	T 596	ft-lb/1000sq.in.	70		
Moisture	t 412	%	5.3		
GE Brightness (coated side)	T 452	%	92		
Whiteness CIE (coated side)	ISO 11475	%	122		
Gloss (coated side)	T 480	%	51		
Parker Print (coated side)	ISO 8791	%	1.1		
Sheffield (coated side)	T 538	Sheffield	10	20	40



The mark of responsible forestry



April 2015

