

# Uniboard S

**Bold lines indicate EBB stock range**

Other Lines are mill makings only (minimum 2.5 tonnes per item, 25-30days)

Uniboard S data sheet												
Description	Specification	Unit	Technical detail									
<b>Thickness</b>	<b>ISO 534</b>	<b>caliper</b>	350	<b>380</b>	410	<b>450</b>	<b>490</b>	510	545	<b>580</b>	640	710
Substance	ISO 536	gsm	280	<b>300</b>	320	<b>350</b>	<b>380</b>	400	425	<b>450</b>	500	550
Stiffness L&W 5° - MD	DIN 53121	Nmm	20.2	<b>24.5</b>	30.1	<b>37.6</b>	<b>47.2</b>	53.6	63.1	<b>72.5</b>	94.8	119.7
Stiffness L&W 5° - CD	DIN 53121	Nmm	7.6	<b>9.1</b>	11.3	<b>14.6</b>	<b>18.7</b>	21.5	26.1	<b>30.6</b>	41.1	50.7
Brightness	ISO 2470-02	%	81									